

Product Texts

Base Polymer	Polyamide 6
Filler/Additive System	30 % glass fibres
Special Features	easy release (demoulding), impact modified, injection moulding grade, heat stabilised
Typical Applications	housings

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	8300 / 4800	MPa	ISO 527
^[C] Stress at break	135 / 80	MPa	ISO 527
^[C] Strain at break	3.3 / 10	%	ISO 527
^[C] Charpy impact strength, +23°C	75 / 90	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	17 / 25	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	210 / *	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1320 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Applications

Encapsulation

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Regional Availability

North America, Europe, Asia Pacific, Near East/Africa

Other text information**Injection molding**

Pre-Drying Conditions	80 °C in a dry air (dessiccant) dryer for 2-12 h dependant on moisture content max. moisture content <0,15 %
Processing Injection Moulding	melt temperature 270-290 °C mould temperature 80-100 °C
Storage	dry, protected from light