

**Product Texts**

Injection Molding, 30% Glass Reinforced, Improved Impact

ISO 1043 PA6-I-GF30

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	0.2 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	0.5 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	9000 / 5000	MPa	ISO 527
<sup>[C]</sup> Stress at break	160 / 95	MPa	ISO 527
<sup>[C]</sup> Strain at break	3.4 / 7.5	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	85 / 85	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	65 / 60	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	15 / 20	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	10 / 10	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Puncture - maximum force, +23°C	935 / -	N	ISO 6603-2
<sup>[C]</sup> Puncture - maximum force, -30°C	770 / -	N	ISO 6603-2
<sup>[C]</sup> Puncture energy, +23°C	3.8 / -	J	ISO 6603-2
<sup>[C]</sup> Puncture energy, -30°C	2.5 / -	J	ISO 6603-2

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	220 / *	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	195 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	210 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	20 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	90 / *	E-6/K	ISO 11359-1/-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
<sup>[C]</sup> Density	1360 / -	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

Test specimen production	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Injection Molding, melt temperature	280	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 6	h	-
Processing humidity	≤0.12	%	-
Melt temperature	260 - 290	°C	-
Mold temperature	80 - 100	°C	-

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

High impact or impact modified

**Delivery form**

Pellets

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America,  
Near East/Africa

**Other text information**

**Injection molding**

**PREPROCESSING**

Residual moisture content: 0.03 - 0.12%

Drying temperature dry air dryer: 80 °C

Drying time dry air dryer 2 - 6 h

**PROCESSING**

Melt temperature (Tmin - Tmax): 260 - 290 °C

Mold temperature: 80 - 100 °C