

Product Texts

Injection Molding, 30% Glass Reinforced, Improved Impact

ISO 1043 PA6-I-GF30

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	9300 / 5100	MPa	ISO 527
^[C] Stress at break	155 / 100	MPa	ISO 527
^[C] Strain at break	4.2 / 11.5	%	ISO 527
^[C] Charpy impact strength, +23°C	95 / -	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	85 / -	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	12 / -	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	10 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	220 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	205 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	222 / *	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1360 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Test specimen production	Value	Unit	Test Standard
ISO Data			
^[C] Injection Molding, melt temperature	280	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 6	h	-
Processing humidity	≤0.12	%	-
Melt temperature	260 - 280	°C	-
Mold temperature	80 - 100	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

High impact or impact modified

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information**Injection molding**

PREPROCESSING

Residual moisture content: 0.03 - 0.12%

Drying temperature dry air dryer: 80 °C

Drying time dry air dryer 2 - 6 h

PROCESSING

Melt temperature (Tmin - Tmax): 260 - 280 °C

Mold temperature: 80 - 100 °C