

Product Texts

Improved Impact, Glass Reinforced

ISO 1043 PA6-I-GF30

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	14 / *	cm ³ /10min	ISO 1133
Temperature	250 / *	°C	-
Load	5 / *	kg	-

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	220 / *	°C	ISO 11357-1/-3

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	1.8 / *	%	Sim. to ISO 62
^[C] Density	1330 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Special Characteristics

High impact or impact modified

Delivery form

Pellets, Black

Regional Availability

Asia Pacific

Other text information**Injection molding**[Steel recommendations for molds screws and barrels](#)[Trouble shooting guideline for injection molding](#)