

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	1.0 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.3 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	3400 / -	MPa	ISO 527
^[C] Stress at break	65 / -	MPa	ISO 527
^[C] Strain at break	41.4 / -	%	ISO 527
^[C] Charpy notched impact strength, +23°C	10.5 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	6.5 / *	%	Sim. to ISO 62
^[C] Humidity absorption	1.6 / *	%	Sim. to ISO 62
^[C] Density	- / 1270	kg/m ³	ISO 1183

[C]: CAMPUS