

**Product Texts**

Polyamide 6 containing recycled material, 20 mineral reinforced, available in black or grey color, also available Heat Stabilized (H) and UV Stabilized (UV).

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Molding shrinkage, parallel	0.9	%	ISO 294-4, 2577
Molding shrinkage, normal	1.1	%	ISO 294-4, 2577

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Yield stress	52	MPa	ISO 527
Strain at break	5	%	ISO 527
Flexural modulus, 23°C	3700	MPa	ISO 178
Charpy impact strength, +23°C	70	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	6.5	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	6.5	kJ/m <sup>2</sup>	ISO 180/1A

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	85	°C	ISO 75-1/-2
Vicat softening temperature, B	200	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.2	mm	-
Burning rate, FMVSS, Thickness 1 mm	100	mm/min	ISO 3795 (FMVSS 302)
Glow Wire Flammability Index (GWFI)	650	°C	IEC 60695-2-12
GWFI - thickness tested (1)	2	mm	-

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1280	kg/m <sup>3</sup>	ISO 1183

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	75	°C	-
Pre-drying - Time	3 - 4	h	-
Processing humidity	≤0.12	%	-
Melt temperature	240 - 270	°C	-
Mold temperature	70 - 90	°C	-
Zone 1	220 - 230	°C	-
Zone 2	230 - 245	°C	-
Zone 3	250 - 260	°C	-
Nozzle temperature	250 - 260	°C	-
Screw speed	50 - 80	rpm	-
Back pressure	0.4 - 0.8	MPa	-
Holding pressure	6 - 8	MPa	-

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Black

**Certifications**

Recycled Resin Content

**Regional Availability**

Europe

**Special Characteristics**

U.V. stabilized or stable to weather, Heat stabilized or stable to heat