

Vampamid 6 3025 V0 DF

PA6-MX30

VAMP TECH SPA

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.009	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.008	mm/mm	ASTM D 955
Mechanical properties			
ISO Data			
Izod impact strength, +23°C	20	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	3	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	7500	MPa	ASTM D 638
Tensile Strength at Yield	55	MPa	ASTM D 638
Elongation at Break	2	%	ASTM D 638
Thermal properties			
ISO Data			
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
ASTM Data			
DTUL @ 264 psi	150	°C	ASTM D 648
Vicat Temperature	190	°C	ASTM D 1525
Electrical properties			
ISO Data			
Comparative tracking index	400	-	IEC 60112
Other properties			
Density	1600	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	90	°C	-
Pre-drying - Time	3	h	-
Melt temperature	250	°C	-
Mold temperature	100	°C	-

Characteristics**Processing**

Injection Molding

Certifications

RoHS compliant

Special Characteristics

Flame retardant

Regional Availability

Europe