

**Staramide BK8**

PA6-MX40

Eurostar Engineering Plastics

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>5800</b>	MPa	ISO 527
Stress at break	<b>90</b>	MPa	ISO 527
Strain at break	<b>6</b>	%	ISO 527
Izod notched impact strength, +23°C	<b>6</b>	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	<b>5</b>	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	<b>-40</b>	°C	-
Rockwell hardness	<b>L 112</b>	-	ISO 2039-2

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>113</b>	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	<b>225</b>	°C	ISO 75-1/-2
Oxygen index	<b>26</b>	%	ISO 4589-1/-2
<b>ASTM Data</b>			
UL 94 Flame rating	<b>HB</b>	-	UL 94
Thickness tested	<b>1.6</b>	mm	-

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1460</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding, Other Extrusion

**Features**

Low Odor

**Delivery form**

Pellets

**Regional Availability**

Europe