

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
Molding shrinkage, normal	0.4	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	9100	MPa	ISO 527
Stress at break	60	MPa	ISO 527
Strain at break	0.7	%	ISO 527
Charpy impact strength, +23°C	15	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	2	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	145	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	190	°C	ISO 75-1/-2
Vicat softening temperature, B	170	°C	ISO 306
Electrical properties			
ASTM Data			
Surface Resistivity	1E12	Ohm	ASTM D 257
Other properties			
Density	2450	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	90 - 100	°C	-
Pre-drying - Time	3	h	-
Melt temperature	240 - 280	°C	-
Mold temperature	80 - 100	°C	-

Characteristics

Processing

Injection Molding

Regional Availability

Europe