

Product Texts

LNP LUBRICOMP RFL32 compound is based on Nylon 6/6 resin containing 10% glass fiber, 15% PTFE. Added features of this grade include: Wear Resistant.

UL Yellow Card Link [E121562-101344610](https://www.ulprospector.com/101344610)

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.6	mm/mm	ASTM D 955
Mold Shrinkage, TD	2	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	5500	MPa	ISO 527
Stress at break	103	MPa	ISO 527
Strain at break	2.7	%	ISO 527
Flexural modulus	5010	MPa	ISO 178
Flexural strength	159	MPa	ISO 178
Izod impact strength, +23°C, 4mm	25	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	4	kJ/m ²	ISO 180/1A

ASTM Data			
Tensile Modulus	5630	MPa	ASTM D 638
Tensile Strength at Break	107	MPa	ASTM D 638
Elongation at Break	2.8	%	ASTM D 638
Flexural Modulus	5300	MPa	ASTM D 790
Izod Impact notched, 1/8 in	46	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	393	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	240	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	257	°C	ISO 75-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
ASTM Data			
Coefficient of Thermal Expansion, MD	47	E-6/K	ASTM D 696
Coefficient of Thermal Expansion, TD	86	E-6/K	ASTM D 696
DTUL @ 66 psi	260	°C	ASTM D 648
DTUL @ 264 psi	246	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Humidity absorption	0.97	%	Sim. to ISO 62
Water Absorption, 24hr	0.64	%	ASTM D 570
Density	1340	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.25	%	-
Melt temperature	280 - 305	°C	-
Mold temperature	95 - 110	°C	-
Zone 1	265 - 275	°C	-
Zone 2	280 - 295	°C	-
Zone 3	295 - 305	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific