

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	3.7	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
<b>ASTM Data</b>			
Melt Flow Index, MFI	3.7	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	94	°C	ISO 11357-1/-3
<b>ASTM Data</b>			
Melting Temperature	94	°C	ASTM D 3418
<b>Other properties</b>			
Density	932	kg/m <sup>3</sup>	ISO 1183
Density	932	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Processing**

Blown Film Extrusion, Film Extrusion

**Delivery form**

Pellets

**Features**

Good Adhesion, Heat Sealable, Copolymer

**Certifications**

Food contact, Food approval FDA 21 CFR

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa