

**RTP 281 AR 10**

PA66-(CF+AF)10

RTP Company

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.003</b>	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Modulus	<b>9308</b>	MPa	ASTM D 638
Tensile Strength	<b>128</b>	MPa	ASTM D 638
Flexural Modulus	<b>7239</b>	MPa	ASTM D 790
Flexural Strength	<b>207</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>42.7</b>	J/m	ASTM D 256
<b>Electrical properties</b>			
<b>ASTM Data</b>			
Volume Resistivity	<b>100000</b>	Ohm*cm	ASTM D 257
<b>Other properties</b>			
Density	<b>1200</b>	kg/m <sup>3</sup>	ASTM D 792
Moisture Content	<b>0.2</b>	%	-
<b>Processing Recommendation Injection Molding</b>			
Pre-drying - Temperature	<b>79.4</b>	°C	-
Pre-drying - Time	<b>4</b>	h	-
Melt temperature	<b>277 - 299</b>	°C	-
Mold temperature	<b>65.6 - 107</b>	°C	-
Injection pressure	<b>68.9 - 124</b>	MPa	-

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America, Europe, Asia Pacific