

**POLIMID STAT A 1010 GFC**

PA66-(CF+GF)20

Poliblend S.p.a.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Molding shrinkage, parallel	<b>0.4</b>	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	<b>9000</b>	MPa	ISO 527
Yield stress	<b>120</b>	MPa	ISO 527
Stress at break	<b>120</b>	MPa	ISO 527
Strain at break	<b>2</b>	%	ISO 527
Izod impact strength, +23°C	<b>35</b>	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C	<b>6</b>	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>260</b>	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	<b>248</b>	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	<b>258</b>	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn. Thickness tested	<b>HB</b> <b>1.5</b>	class mm	IEC 60695-11-10 -
Burning behav. at thickness h Thickness tested	<b>HB</b> <b>3.0</b>	class mm	IEC 60695-11-10 -
<b>Electrical properties</b>			
<b>ISO Data</b>			
Volume resistivity	<b>10</b>	Ohm*m	IEC 62631-3-1
<b>Other properties</b>			
Density	<b>1250</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Special Characteristics**

Increased electrical conductivity, Anti-static

**Regional Availability**

Europe