

XEBRID 1-C30-G30

PA66-(CF+GF)60

Xenia Srl

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.1	%	ISO 294-4, 2577
Molding shrinkage, normal	0.2	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	32500	MPa	ISO 527
Stress at break	245	MPa	ISO 527
Strain at break	1.5	%	ISO 527
Flexural modulus, 23°C	25000	MPa	ISO 178
Flexural strength	350	MPa	ISO 178
Izod impact strength, +23°C	54	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	10	kJ/m ²	ISO 180/1A
Izod notched impact strength Temperature	8 -30	kJ/m ² °C	ISO 180/1A -
Thermal properties			
ISO Data			
Temp. of deflection under load, 8.00 MPa	210	°C	ISO 75-1/-2
Vicat softening temperature, B	245	°C	ISO 306
Electrical properties			
ISO Data			
Volume resistivity	0.01	Ohm*m	IEC 62631-3-1
Surface resistivity	1000	Ohm	IEC 62631-3-2
Other properties			
Density	1560	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80 - 100	°C	-
Pre-drying - Time	6 - 8	h	-
Melt temperature	265 - 280	°C	-
Mold temperature	110	°C	-

Characteristics**Processing**

Injection Molding

Regional Availability

Europe