

RTP 299 X 123319 B

PA66-(CF+MED(Ni))

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.002	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	11720	MPa	ASTM D 638
Tensile Strength	100	MPa	ASTM D 638
Flexural Modulus	11030	MPa	ASTM D 790
Flexural Strength	134	MPa	ASTM D 790
Izod Impact notched, 1/8 in	42.7	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.59	mm	-

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	100000	Ohm	ASTM D 257
Volume Resistivity	1	Ohm*cm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1330	kg/m ³	ASTM D 792
Moisture Content	0.2	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	79.4	°C	-
Pre-drying - Time	4	h	-
Melt temperature	277 - 299	°C	-
Mold temperature	65.6 - 107	°C	-
Injection pressure	68.9 - 124	MPa	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Flame retardant

Features

EMI Attenuation/Shielding

Regional Availability

North America, Europe, Asia Pacific