

| Processing/Physical Characteristics        | dry / cond     | Unit | Test Standard   |
|--|----------------|------|-----------------|
| <b>ISO Data</b>                            |                |      |                 |
| <sup>[C]</sup> Molding shrinkage, parallel | <b>0.3 / *</b> | %    | ISO 294-4, 2577 |
| <sup>[C]</sup> Molding shrinkage, normal   | <b>0.7 / *</b> | %    | ISO 294-4, 2577 |

[C]: CAMPUS

| Mechanical properties          | dry / cond      | Unit | Test Standard |
|--------------------------------|-----------------|------|---------------|
| <b>ISO Data</b>                |                 |      |               |
| <sup>[C]</sup> Tensile Modulus | <b>9500 / -</b> | MPa  | ISO 527       |
| <sup>[C]</sup> Stress at break | <b>145 / -</b>  | MPa  | ISO 527       |
| <sup>[C]</sup> Strain at break | <b>2.7 / -</b>  | %    | ISO 527       |

[C]: CAMPUS

| Electrical properties              | dry / cond     | Unit  | Test Standard |
|------------------------------------|----------------|-------|---------------|
| <b>ISO Data</b>                    |                |       |               |
| <sup>[C]</sup> Volume resistivity  | <b>1E9 / -</b> | Ohm*m | IEC 62631-3-1 |
| <sup>[C]</sup> Surface resistivity | <b>* / 1E9</b> | Ohm   | IEC 62631-3-2 |

[C]: CAMPUS

| Other properties                   | dry / cond      | Unit              | Test Standard  |
|------------------------------------|-----------------|-------------------|----------------|
| <sup>[C]</sup> Water absorption    | <b>4.5 / *</b>  | %                 | Sim. to ISO 62 |
| <sup>[C]</sup> Humidity absorption | <b>1.3 / *</b>  | %                 | Sim. to ISO 62 |
| <sup>[C]</sup> Density             | <b>- / 1260</b> | kg/m <sup>3</sup> | ISO 1183       |

[C]: CAMPUS

**Characteristics**

**Delivery form**

Black

**Regional Availability**

Europe

**Special Characteristics**

Anti-static