

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>14600 / -</b>	MPa	ISO 527
<sup>[C]</sup> Stress at break	<b>210 / -</b>	MPa	ISO 527
<sup>[C]</sup> Strain at break	<b>2.3 / -</b>	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	<b>65.7 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>8 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Density	<b>- / 1330</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics**

**Delivery form**

Black