

4MID 9A22325 I

PA66-(GF+GB)25

4Plas

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	6000	MPa	ISO 527
Stress at break	110	MPa	ISO 527
Strain at break	3	%	ISO 527
Izod notched impact strength, +23°C	7	kJ/m ²	ISO 180/1A
Izod notched impact strength	6	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	262	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	235	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E13	Ohm	IEC 62631-3-2
Comparative tracking index	500	-	IEC 60112

Other properties	Value	Unit	Test Standard
Density	1290	kg/m ³	ISO 1183
Moisture Content	0.2	%	-

Characteristics**Special Characteristics**

High impact or impact modified

Regional Availability

Europe