

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	7100 / 5100	MPa	ISO 527
Stress at break	145 / 105	MPa	ISO 527
Strain at break	3.5 / 4.5	%	ISO 527
Charpy impact strength, +23°C	38 / 48	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	35 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	7 / 12	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	6 / -	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	6 / 10	kJ/m ²	ISO 180/1A
Izod notched impact strength	4 / -	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	262 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	240 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	240 / *	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-
Burning behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
Relative permittivity, 1MHz	3.5 / 5.5	-	IEC 62631-2-1
Dissipation factor, 1MHz	150 / 1900	E-4	IEC 62631-2-1
Volume resistivity	1E13 / 1E10	Ohm*m	IEC 62631-3-1
Surface resistivity	* / 1E10	Ohm	IEC 62631-3-2
Comparative tracking index	500 / -	-	IEC 60112

Other properties	dry / cond	Unit	Test Standard
Water absorption	6 / *	%	Sim. to ISO 62
Humidity absorption	2 / *	%	Sim. to ISO 62
Density	1360 / -	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa