

**Tislamid® B 30D03D05 R01**

PA66-(GF+GB)30

Tisan Engineering Plastics Co.Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Molding shrinkage, normal	0.4	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	7000	MPa	ISO 527
Stress at break	140	MPa	ISO 527
Strain at break	2.5	%	ISO 527
Izod impact strength, +23°C	52.5	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C	7	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength Temperature	6 -30	kJ/m <sup>2</sup> °C	ISO 180/1A -

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	263	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	250	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	260	°C	ISO 75-1/-2
Vicat softening temperature, B	250	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn. Thickness tested	HB 1.6	class mm	IEC 60695-11-10 -
Burning behav. at thickness h Thickness tested	HB 0.8	class mm	IEC 60695-11-10 -

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E13	Ohm	IEC 62631-3-2
Comparative tracking index	500	-	IEC 60112

Other properties	Value	Unit	Test Standard
Density	1360	kg/m <sup>3</sup>	ISO 1183
Moisture Content	0.2	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	90 - 100	°C	-
Pre-drying - Time	3 - 4	h	-
Processing humidity	≤0.2	%	-
Melt temperature	260 - 290	°C	-
Mold temperature	70 - 110	°C	-
Zone 1	260 - 280	°C	-
Zone 2	260 - 280	°C	-
Zone 3	260 - 280	°C	-
Nozzle temperature	250 - 270	°C	-
Back pressure	50 - 100	MPa	-

**Characteristics****Processing**

Injection Molding

**Regional Availability**

Europe, Near East/Africa

**Delivery form**

Pellets, Natural Color