

HILOY 626

PA66-(GF+MX)35

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.003	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	125	MPa	ASTM D 638
Flexural Modulus	8632	MPa	ASTM D 790
Flexural Strength	199	MPa	ASTM D 790
Izod Impact notched, 1/8 in	37.4	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	251	°C	ASTM D 648
DTUL @ 264 psi	251	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1430	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

North America

Special Characteristics

Heat stabilized or stable to heat