

PRL NY66-M25G15-(color)H

PA66-(GF+MX)40

Polymer Resources, Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0065	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	131	MPa	ASTM D 638
Tensile Strength at Break	131	MPa	ASTM D 638
Flexural Modulus	6.895	MPa	ASTM D 790
Flexural Strength	179	MPa	ASTM D 790
Izod Impact notched, 1/8 in	53.4	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	254	°C	ASTM D 648
DTUL @ 264 psi	235	°C	ASTM D 648
Other properties			
Density	1490	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	73.9 - 85	°C	-
Pre-drying - Time	3 - 4	h	-
Melt temperature	288 - 304	°C	-
Mold temperature	82.2 - 104	°C	-
Zone 1	271 - 282	°C	-
Zone 2	282 - 299	°C	-
Zone 3	282 - 304	°C	-

Characteristics**Processing**

Injection Molding, Other Extrusion

Delivery form

Pellets

Additives

Lubricants

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

North America