

Product Texts

LNP LUBRICOMP RFL16 compound is based on Nylon 6/6 resin containing 30% glass fiber, 5% PTFE. Added features of this grade include: Wear Resistant.

UL Yellow Card Link [E207780-103093655](https://www.ul.com/yellow-card/E207780-103093655)

| Mechanical properties | Value | Unit | Test Standard |
|--|--------------|-------------------|----------------------|
| ISO Data | | | |
| Tensile Modulus | 10600 | MPa | ISO 527 |
| Yield stress | 188 | MPa | ISO 527 |
| Yield strain | 2.8 | % | ISO 527 |
| Stress at break | 185 | MPa | ISO 527 |
| Strain at break | 2.7 | % | ISO 527 |
| Flexural modulus | 8980 | MPa | ISO 178 |
| Izod impact strength, +23°C, 4mm | 62 | kJ/m ² | ISO 180/1U |
| Izod notched impact strength, +23°C, 4mm | 10 | kJ/m ² | ISO 180/1A |
| ASTM Data | | | |
| Tensile Modulus | 11020 | MPa | ASTM D 638 |
| Tensile Strength at Break | 189 | MPa | ASTM D 638 |
| Elongation at Break | 2.7 | % | ASTM D 638 |
| Flexural Modulus | 8920 | MPa | ASTM D 790 |
| Izod Impact notched, 1/8 in | 110 | J/m | ASTM D 256 |
| Izod Impact unnotched, 1/8 in | 1070 | J/m | ASTM D 256 |

| Thermal properties | Value | Unit | Test Standard |
|---|--------------|-------------|----------------------|
| ISO Data | | | |
| Temp. of deflection under load, 1.80 MPa | 251 | °C | ISO 75-1/-2 |
| Temp. of deflection under load, 0.45 MPa | 262 | °C | ISO 75-1/-2 |
| Burning behav. at 1.5 mm nom. thickn. Thickness tested | HB | class | IEC 60695-11-10 |
| | 1.5 | mm | - |
| ASTM Data | | | |
| Coefficient of Thermal Expansion, MD | 40 | E-6/K | ASTM D 696 |
| Coefficient of Thermal Expansion, TD | 92 | E-6/K | ASTM D 696 |
| DTUL @ 66 psi | 259 | °C | ASTM D 648 |
| DTUL @ 264 psi | 249 | °C | ASTM D 648 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Humidity absorption | 0.88 | % | Sim. to ISO 62 |
| Density | 1400 | kg/m ³ | ISO 1183 |
| Water Absorption, 24hr | 0.57 | % | ASTM D 570 |
| Density | 1400 | kg/m ³ | ASTM D 792 |

| Processing Recommendation Injection Molding | Value | Unit | Test Standard |
|--|------------------|-------------|----------------------|
| Pre-drying - Temperature | 80 | °C | - |
| Pre-drying - Time | 4 | h | - |
| Processing humidity | ≤0.25 | % | - |
| Melt temperature | 280 - 305 | °C | - |
| Mold temperature | 95 - 110 | °C | - |
| Zone 1 | 265 - 275 | °C | - |
| Zone 2 | 280 - 295 | °C | - |
| Zone 3 | 295 - 305 | °C | - |
| Screw speed | 30 - 60 | rpm | - |
| Back pressure | 0.2 - 0.3 | MPa | - |

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific