

Product Texts

Starflam X-Protect RX07034 is a 30% glass fiber reinforced PA66 PA6 compound. Developed for use in Arc chambers and other injection molding applications, it has low smoke and easy processing.

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Stress at break	170 / -	MPa	ISO 527
^[C] Strain at break	2.3 / -	%	ISO 527

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	213 / *	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1540 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Special Characteristics

Heat stabilized or stable to heat

Delivery form

Pellets

Features

Low Smoke

Additives

Lubricants, Release agent

Regional Availability

North America, Europe