

CELSTRAN® PA66-AF35-01 AF3003 Natural 6MM

PA66-AF35

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	9200	MPa	ISO 527
^[C] Stress at break	125	MPa	ISO 527
^[C] Strain at break	1.95	%	ISO 527
^[C] Charpy notched impact strength, +23°C	14	kJ/m ²	ISO 179/1eA

^[C]: CAMPUS**Characteristics****Delivery form**

Natural Color

Regional Availability

North America, Europe, Asia Pacific