

Product Texts

LNP STAT-KON RX08404 compound is based on Nylon 6/6 resin containing conductive carbon powder. Added features of this grade include: Electrically Conductive, High Impact.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	4	mm/mm	ASTM D 955
Mold Shrinkage, TD	4	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1930	MPa	ISO 527
Stress at break	47	MPa	ISO 527
Strain at break	26	%	ISO 527
Flexural modulus	1850	MPa	ISO 178
Flexural strength	61	MPa	ISO 178
Izod impact strength, +23°C, 4mm	196	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	12	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	1960	MPa	ASTM D 638
Tensile Strength at Break	46	MPa	ASTM D 638
Elongation at Break	26	%	ASTM D 638
Flexural Modulus	1760	MPa	ASTM D 790
Izod Impact notched, 1/8 in	141	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	1720	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	117	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	165	°C	ISO 75-1/-2
ASTM Data			
Coefficient of Thermal Expansion, MD	110	E-6/K	ASTM D 696
Coefficient of Thermal Expansion, TD	114	E-6/K	ASTM D 696
DTUL @ 66 psi	195	°C	ASTM D 648
DTUL @ 264 psi	60	°C	ASTM D 648

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	1000000	Ohm	ASTM D 257
Volume Resistivity	1000000	Ohm*cm	ASTM D 257

Other properties	Value	Unit	Test Standard
Humidity absorption	0.87	%	Sim. to ISO 62
Water Absorption, 24hr	0.6	%	ASTM D 570

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.25	%	-
Melt temperature	280 - 305	°C	-
Mold temperature	95 - 110	°C	-
Zone 1	265 - 275	°C	-
Zone 2	280 - 295	°C	-
Zone 3	295 - 305	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Special Characteristics

Increased electrical conductivity