

Product Texts

Vydyne STAT A 12 FC BK is standard flow 12% carbon-fiber reinforced PA66 resin. Available in black, it is specifically designed for high stiffness and strength. This product is also electrically dissipative.

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.5 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.0 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	9000 / 6300	MPa	ISO 527
^[C] Stress at break	145 / 100	MPa	ISO 527
^[C] Strain at break	3.5 / 6	%	ISO 527

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	260 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	235 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	245 / *	°C	ISO 75-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	10000 / -	Ohm*m	IEC 62631-3-1

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Humidity absorption	2.3 / *	%	Sim. to ISO 62
^[C] Density	1190 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Additives

Lubricants

Delivery form

Pellets, Black

Regional Availability

North America, Europe, Asia Pacific