

Product Texts

LNP THERMOCOMP RC003SXS compound is based on Nylon 6/6 resin containing 15% carbon fiber. Added features of this grade include: Electrically Conductive, Heat Stabilized.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	13000	MPa	ISO 527
Stress at break	170	MPa	ISO 527
Strain at break	2	%	ISO 527
Flexural modulus	10000	MPa	ISO 178
Charpy impact strength, +23°C	45	kJ/m ²	ISO 179/1eU
Izod notched impact strength, +23°C, 4mm	5	kJ/m ²	ISO 180/1A
Rockwell hardness	L105	-	ISO 2039-2

Thermal properties	Value	Unit	Test Standard
ISO Data			
Vicat softening temperature, 120°C/h 50N	255	°C	ISO 306
Coeff. of linear therm. expansion, parallel	20	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	110	E-6/K	ISO 11359-1/-2

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1780	Ohm*m	IEC 62631-3-1
Surface resistivity	178000	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Water absorption	5.5	%	Sim. to ISO 62
Density	1190	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	320 - 360	°C	-
Mold temperature	80 - 100	°C	-
Feed temperature	60 - 90	°C	-
Zone 1	280 - 320	°C	-
Zone 2	320 - 360	°C	-
Zone 3	320 - 360	°C	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Special Characteristics

Increased electrical conductivity