

AKROMID® A3 CF 20 5 black (8081)

PA66-CF20

Akro-Plastic GmbH

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	17100	MPa	ISO 527
Stress at break	240	MPa	ISO 527
Strain at break	2.4	%	ISO 527
Charpy impact strength, +23°C	65	kJ/m ²	ISO 179/1eU

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	260	°C	ISO 11357-1/-3
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-

Other properties	Value	Unit	Test Standard
Density	1200	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	320	°C	-
Mold temperature	100	°C	-
Injection pressure	75	MPa	-

Characteristics**Processing**

Injection Molding

Delivery form

Black

Special Characteristics

Heat stabilized or stable to heat

Features

Tribologic Grade

Regional Availability

Europe, Asia Pacific