

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7 / *	%	ISO 294-4, 2577
Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	16000 / 9500	MPa	ISO 527
Stress at break	190 / 135	MPa	ISO 527
Strain at break	2.5 / 4	%	ISO 527
Flexural modulus, 23°C	14000 / -	MPa	ISO 178
Flexural strength	280 / -	MPa	ISO 178
Charpy impact strength, +23°C	50 / 60	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	40 / -	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	6 / 8	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	4 / -	kJ/m <sup>2</sup>	ISO 179/1eA
Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	262 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	250 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	10 / *	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	90 / *	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-
Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Surface resistivity	* / 10000	Ohm	IEC 62631-3-2
Other properties	dry / cond	Unit	Test Standard
Density	1230 / -	kg/m <sup>3</sup>	ISO 1183
Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	320	°C	-
Mold temperature	100	°C	-
Injection pressure	75	MPa	-

## Characteristics

### Processing

Injection Molding

### Features

Tribologic Grade

### Delivery form

Black

### Regional Availability

Europe, Asia Pacific