

**Product Texts**

Polyamide 66, 30% carbon fiber reinforced, heat-aging stabilized, impact modified, for injection moulding, natural color

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>17500 / -</b>	MPa	ISO 527
<sup>[C]</sup> Stress at break	<b>165 / -</b>	MPa	ISO 527
<sup>[C]</sup> Strain at break	<b>4.6 / -</b>	%	ISO 527
Flexural modulus, 23°C	<b>13000 / -</b>	MPa	ISO 178
<sup>[C]</sup> Charpy impact strength, +23°C	<b>70 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>14 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>262 / *</b>	°C	ISO 11357-1/-3
<sup>[C]</sup> Burning Behav. at thickness h	<b>HB / *</b>	class	IEC 60695-11-10
Thickness tested	<b>0.8 / *</b>	mm	-

[C]: CAMPUS

<b>Electrical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Volume resistivity	<b>10 / -</b>	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	<b>* / 100</b>	Ohm	IEC 62631-3-2

[C]: CAMPUS

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Density	<b>1210 / -</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Delivery form**

Natural Color

**Special Characteristics**

High impact or impact modified, Heat stabilized or stable to heat