

CELSTRAN® PA66-CF40-02 AF3004 Natural

PA66-CF40

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	30860	MPa	ISO 527
^[C] Charpy notched impact strength, +23°C	23	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	260	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1340	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Special Characteristics

Increased electrical conductivity, Anti-static

Delivery form

Pellets, Natural Color

Regional Availability

North America, Europe, Asia Pacific