

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	11	g/10min	ASTM D 1238
Temperature	275	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength	245	MPa	ASTM D 638
Elongation at Break	7	%	ASTM D 638
Flexural Modulus	23540	MPa	ASTM D 790
Flexural Strength	383	MPa	ASTM D 790
Izod Impact notched, 1/8 in	83.4	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	260	°C	ASTM D 648
DTUL @ 264 psi	253	°C	ASTM D 648
Electrical properties			
ASTM Data			
Surface Resistivity	1000	Ohm	ASTM D 257
Other properties			
Density	1310	kg/m ³	ASTM D 792

Characteristics

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

Europe, Asia Pacific