

CELSTRAN® CFR-TP PA66 CF60-02

PA66-CF60

Celanese

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	260	°C	ISO 11357-1/-3
^[C] Glass transition temperature, 10°C/min	50	°C	ISO 11357-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1440	kg/m ³	ISO 1183

[C]: CAMPUS