

Product Texts

Base Polymer	Polyamide 66
Filler/Additive System	20 % glass beads
Special Features	heat stabilised,easy release (demoulding),high surface gloss
Market Segment	various
Application Area	various

Mechanical properties

dry / cond

Unit

Test Standard

ISO Data

[C] Tensile Modulus	3700 / -	MPa	ISO 527
[C] Stress at break	86 / -	MPa	ISO 527
[C] Strain at break	3.5 / -	%	ISO 527
[C] Charpy impact strength, +23°C	25 / -	kJ/m ²	ISO 179/1eU
[C] Charpy notched impact strength, +23°C	3 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties

dry / cond

Unit

Test Standard

ISO Data

[C] Temp. of deflection under load, 1.80 MPa	88 / *	°C	ISO 75-1/-2
--	--------	----	-------------

[C]: CAMPUS

Other properties

dry / cond

Unit

Test Standard

[C] Density	1270 / -	kg/m ³	ISO 1183
-------------	----------	-------------------	----------

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Special Characteristics

Heat stabilized or stable to heat

Other text information**Injection molding**

Pre-Drying Conditions	80 °C in a dry air (dessiccant) dryer for 2-12 h dependant on moisture content max. moisture content <0,15 %
Processing Injection Moulding	melt temperature 280-300 °C mould temperature 80-90 °C
Storage	dry, protected from light not above 30°C