

**Product Texts**

Base Polymer	Polyamide 66
Filler/Additive System	20 % aramid
Special Features	improved sliding / wear, heat stabilised, high stiffness
Market Segment	Automotive, Machinery
Typical Applications	functional components

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>3700 / -</b>	MPa	ISO 527
<sup>[C]</sup> Stress at break	<b>72 / -</b>	MPa	ISO 527
<sup>[C]</sup> Strain at break	<b>2.2 / -</b>	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	<b>15 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>2 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	<b>100 / *</b>	°C	ISO 75-1/-2

[C]: CAMPUS

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Density	<b>1180 / -</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

**Other text information****Injection molding**

Pre-Drying Conditions	in a dry air (dessiccant) dryer <80 °C for 2-12 h dependant on moisture content
Processing Injection Moulding	melt temperature 280-300 °C mould temperature 80-120 °C
Storage	dry, protected from light not above 30°C