

ECOMID® A GF13 BK 9005/1

PA66-GF13

Celanese

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	241	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	257	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1210	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Delivery form**

Black

Certifications

Recycled Resin Content