

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.0	%	ISO 294-4, 2577
Molding shrinkage, normal	1.1	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	95	MPa	ISO 527
Flexural modulus, 23°C	4100	MPa	ISO 178
Flexural strength	125	MPa	ISO 178

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	260	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	210	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	1190	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Applications

Automotive

Special Characteristics

High impact or impact modified

Regional Availability

North America