

QUALINYL PA66 GF 14

PA66-GF14

Qualchem Zrt.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	75	MPa	ISO 527
Yield strain	4	%	ISO 527
Stress at break	70	MPa	ISO 527
Strain at break	9	%	ISO 527

Characteristics

Regional Availability

Europe