

**Product Texts**

15% Glass Reinforced, Heat Stabilized

ISO 1043 PA66-GF15

<b>Processing/Physical Characteristics</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	<b>1.0 / *</b>	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	<b>1.5 / *</b>	%	ISO 294-4, 2577

[C]: CAMPUS

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>6500 / 4000</b>	MPa	ISO 527
<sup>[C]</sup> Stress at break	<b>115 / 80</b>	MPa	ISO 527
<sup>[C]</sup> Strain at break	<b>3 / 6</b>	%	ISO 527
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>5 / 8</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	<b>3.5 / 3.5</b>	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>260 / *</b>	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	<b>240 / *</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	<b>255 / *</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	<b>HB / *</b>	class	IEC 60695-11-10
Thickness tested	<b>1.5 / *</b>	mm	-
Yellow Card available	<b>yes / *</b>	-	-
<sup>[C]</sup> Burning Behav. at thickness h	<b>HB / *</b>	class	IEC 60695-11-10
Thickness tested	<b>3.0 / *</b>	mm	-
Yellow Card available	<b>yes / *</b>	-	-

[C]: CAMPUS

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Water absorption	<b>7.8 / *</b>	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	<b>2 / *</b>	%	Sim. to ISO 62
<sup>[C]</sup> Density	<b>1250 / *</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

Heat stabilized or stable to heat

**Delivery form**

Pellets

**Regional Availability**

North America, Europe

**Additives**

Lubricants, Release agent

**Other text information****Injection molding**[Injection Molding Recommendations](#)[Steel recommendations for molds screws and barrels](#)[Trouble shooting guideline for injection molding](#)