

**Product Texts**

BERGAMID A70G15 TM-Z, PA66 reinforced  
15% glass fibre,  
impact modified, very good impact strength

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	4600 / 4700	MPa	ISO 527
Stress at break	70 / 90	MPa	ISO 527
Strain at break	5 / 3	%	ISO 527
Charpy impact strength, +23°C	75 / 65	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	65 / 55	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	14 / 11	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	8 / 8	kJ/m <sup>2</sup>	ISO 179/1eA

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melting temperature, 10°C/min	261 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	235 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	250 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	34 / *	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	73 / *	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-
Burning behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

<b>Electrical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Relative permittivity, 1MHz	5 / 3.6	-	IEC 62631-2-1
Dissipation factor, 1MHz	1600 / 140	E-4	IEC 62631-2-1
Volume resistivity	1E10 / 1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	* / 1E10	Ohm	IEC 62631-3-2
Electric strength	75 / 90	kV/mm	IEC 60243-1
Comparative tracking index	500 / -	-	IEC 60112

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
Water absorption	6.2 / *	%	Sim. to ISO 62
Humidity absorption	2 / *	%	Sim. to ISO 62
Density	- / 1220	kg/m <sup>3</sup>	ISO 1183

<b>Material specific properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Viscosity number	160 / *	cm <sup>3</sup> /g	ISO 307, 1157, 1628

<b>Test specimen production</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Injection Molding, melt temperature	280	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294

**Characteristics****Processing**

Injection Molding

**Regional Availability**

Europe

**Delivery form**

Pellets

**Other text information**

**Injection Molding**

PREPROCESSING

Max. Water Content 0,1%

Pre-Drying: 80°C 4 Hours

PROCESSING

Melt Temperature 280-300°C

Mould Temperature 80-90°C