

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	6500 / 4500	MPa	ISO 527
Tensile Strength	125 / 85	MPa	ISO 527
Strain at break	4 / 6	%	ISO 527
Charpy impact strength, +23°C	43 / 60	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	6 / 9	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	230 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	250 / *	°C	ISO 75-1/-2
Burning behav. at thickness h	HB / *	class	IEC 60695-11-10
Electrical properties			
ISO Data			
Surface resistivity	* / 1E12	Ohm	IEC 62631-3-2
Electric strength	32 / -	kV/mm	IEC 60243-1
Other properties			
Water absorption	1 / *	%	Sim. to ISO 62
Density	1240 / -	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Additives

Lubricants

Delivery form

Pellets, Natural Color

Regional Availability

Europe