

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	5500 / 3800	MPa	ISO 527
Tensile Strength	115 / 70	MPa	ISO 527
Strain at break	4 / 6	%	ISO 527
Charpy impact strength, +23°C	39 / 52	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	5 / 8	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	230 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	250 / *	°C	ISO 75-1/-2
Burning behav. at thickness h	V-0 / *	class	IEC 60695-11-10
Electrical properties			
ISO Data			
Surface resistivity	* / 1E12	Ohm	IEC 62631-3-2
Electric strength	32 / -	kV/mm	IEC 60243-1
Other properties			
Water absorption	0.7 / *	%	Sim. to ISO 62
Density	1270 / -	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Delivery form

Pellets, Black

Additives

Lubricants

Special Characteristics

Flame retardant

Applications

Electrical and Electronical

Regional Availability

Europe