

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	8900 / 6800	MPa	ISO 527
^[C] Stress at break	160 / 110	MPa	ISO 527
^[C] Strain at break	3.5 / 6	%	ISO 527
^[C] Charpy impact strength, +23°C	80 / 84	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	75 / -	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	12 / 14	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	9.3 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	191 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	207 / *	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	204 / *	°C	ISO 306

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1300 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Regional Availability

Europe, Near East/Africa