

**Product Texts**

Zytel® LCPA long chain polyamide resins provide an innovative and growing portfolio of flexible polymers with excellent thermal, chemical, and hydrolysis resistance. The diverse selection of Zytel® LCPA grades is targeted for a range of performance characteristics, balancing temperature resistance, flexibility and low permeation.

**Zytel® 77G33HS1L NC010 is a 33% glass reinforced, heat stabilized, polyamide 612 resin.**

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	0.9 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Thermal conductivity of melt	0.26	W/(m K)	-
<sup>[C]</sup> Ejection temperature	210	°C	-
<b>ASTM Data</b>			
Mold Shrinkage, MD	0.001	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.009	mm/mm	ASTM D 955

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	9500 / 8000	MPa	ISO 527
<sup>[C]</sup> Stress at break	170 / 140	MPa	ISO 527
<sup>[C]</sup> Strain at break	3 / 3.2	%	ISO 527
Flexural modulus, 23°C	8200 / 7000	MPa	ISO 178
<sup>[C]</sup> Charpy impact strength, +23°C	80 / 90	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	60 / 65	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	13 / 12	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	11 / 10	kJ/m <sup>2</sup>	ISO 179/1eA
Izod impact strength, +23°C	70 / -	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C	13 / 12	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	11 / 10	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-30	°C	-
<b>ASTM Data</b>			
Tensile Strength	165 / -	MPa	ASTM D 638
Elongation at Break	3 / -	%	ASTM D 638
Flexural Modulus	8270 / -	MPa	ASTM D 790
Flexural Strength	255 / -	MPa	ASTM D 790
Rockwell Hardness	R 118 /	-	ASTM D 785

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	218 / *	°C	ISO 11357-1/-3
<sup>[C]</sup> Glass transition temperature, 10°C/min	65 / *	°C	ISO 11357-1/-2
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	200 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	216 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	20 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	110 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	-
Yellow Card available	yes / *	-	-
<sup>[C]</sup> Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-
Yellow Card available	yes / *	-	-
<b>ASTM Data</b>			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.5	mm	-
DTUL @ 264 psi	210	°C	ASTM D 648

Melting Temperature	217	°C	ASTM D 3418
---------------------	-----	----	-------------

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Volume resistivity	1E13 / -	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Comparative tracking index	600 / -	-	IEC 60112
<b>ASTM Data</b>			
Dielectric Strength, Short Time	0.807 / -	kV/mm	ASTM D 149
Dissipation Factor, 1 MHz	0.02 / -	-	ASTM D 150
Dielectric Constant, 1 MHz	3.4 / -	-	ASTM D 150
Surface Resistivity	* / 1E15	Ohm	ASTM D 257
Volume Resistivity	1E15 / -	Ohm*cm	ASTM D 257

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
<sup>[C]</sup> Water absorption	1.8 / *	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	0.7 / *	%	Sim. to ISO 62
<sup>[C]</sup> Density	1320 / -	kg/m <sup>3</sup>	ISO 1183
Water Absorption, 24hr	0.16	%	ASTM D 570
Water Absorption, Equilibrium	2	%	ASTM D 570
Density	1320	kg/m <sup>3</sup>	ASTM D 792

[C]: CAMPUS

## Characteristics

### Processing

Injection Molding

### Delivery form

Pellets, Natural Color

### Additives

Lubricants

### Special Characteristics

Heat stabilized or stable to heat

### Features

Weldable

### Applications

Automotive, Electrical and Electronical

### Regional Availability

North America, Europe, Asia Pacific, South and Central America