

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.0065</b>	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength	<b>108</b>	MPa	ASTM D 638
Flexural Modulus	<b>5680</b>	MPa	ASTM D 790
Flexural Strength	<b>168</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 120</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>29</b>	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
UL 94 Flame rating	<b>HB</b>	-	UL 94
Coefficient of Thermal Expansion, MD	<b>30</b>	E-6/K	ASTM D 696
DTUL @ 66 psi	<b>245</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>235</b>	°C	ASTM D 648
Melting Temperature	<b>255</b>	°C	ASTM D 3418

Electrical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Dielectric Strength, Short Time	<b>21</b>	kV/mm	ASTM D 149
Dielectric Constant, 1 MHz	<b>3.6</b>	-	ASTM D 150
Arc Resistance	<b>135</b>	s	ASTM D 495

Other properties	Value	Unit	Test Standard
Density	<b>1240</b>	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Delivery form

Black

### Regional Availability

North America, Asia Pacific

### Special Characteristics

U.V. stabilized or stable to weather, Heat stabilized or stable to heat