

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.004</b>	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Tensile Strength at Yield	<b>124</b>	MPa	ASTM D 638
Elongation at Break	<b>3.1</b>	%	ASTM D 638
Flexural Modulus	<b>5514</b>	MPa	ASTM D 790
Flexural Strength	<b>200</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 120</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>80</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
UL 94 Flame rating	<b>HB</b>	-	UL 94
Thickness tested	<b>3.2</b>	mm	-
Coefficient of Thermal Expansion, MD	<b>40</b>	E-6/K	ASTM D 696
DTUL @ 264 psi	<b>240</b>	°C	ASTM D 648
Melting Temperature	<b>260</b>	°C	ASTM D 3418
<b>Electrical properties</b>			
<b>ASTM Data</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Dielectric Strength, Short Time	<b>26</b>	kV/mm	ASTM D 149
Volume Resistivity	<b>3E13</b>	Ohm*cm	ASTM D 257
Arc Resistance	<b>110</b>	s	ASTM D 495
<b>Other properties</b>			
<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>	
Water Absorption, 24hr	<b>2.8</b>	%	ASTM D 570
Density	<b>1220</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Certifications**

RoHS compliant

**Regional Availability**

Europe, Asia Pacific