

Matrixx F662E15

PA66-GF15

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	106	MPa	ASTM D 638
Elongation at Yield	9	%	ASTM D 638
Flexural Modulus	5000	MPa	ASTM D 790
Izod Impact notched, 1/8 in	36	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1220	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	71 - 82	°C	-
Pre-drying - Time	4 - 6	h	-
Melt temperature	260 - 282	°C	-
Mold temperature	66 - 93	°C	-
Zone 1	249 - 271	°C	-
Zone 2	249 - 271	°C	-
Zone 3	249 - 271	°C	-
Back pressure	<0.345	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America

Delivery form

Pellets