

Polybest 66 PD GF15

PA66-GF15

Polyma Kunststoff GmbH & Co.KG

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	7000	MPa	ISO 527
Yield strain	4	%	ISO 527
Stress at break	125	MPa	ISO 527
Strain at break	4.5	%	ISO 527
Izod impact strength, +23°C	40	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	7.5	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	260	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	240	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	250	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Glow Wire Flammability Index (GWFI)	650	°C	IEC 60695-2-12
GWFI - thickness tested (1)	2	mm	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Comparative tracking index	600	-	IEC 60112

Other properties	Value	Unit	Test Standard
Humidity absorption	1	%	Sim. to ISO 62
Density	1240	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 90	°C	-
Pre-drying - Time	3	h	-
Melt temperature	265 - 275	°C	-
Mold temperature	70 - 80	°C	-

Characteristics**Processing**

Injection Molding

Regional Availability

Europe

Delivery form

Natural Color