

Mechanical properties	dry / cond	Unit	Test Standard
ASTM Data			
Tensile Strength	121 / -	MPa	ASTM D 638
Elongation at Break	2 / -	%	ASTM D 638
Flexural Modulus	5170 / -	MPa	ASTM D 790
Flexural Strength	176 / -	MPa	ASTM D 790
Izod Impact notched, 1/8 in	64 / -	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	243	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1250	kg/m ³	ASTM D 792

Characteristics

Delivery form

Pellets

Regional Availability

North America

Additives

Lubricants